AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) | Date: 18-11-2021

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	06-11-2021
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 7 Days Compressive Strength
Date of Test	18-11-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	06-11-2021	18-11-2021	150x150x150	22500	456	16.3	16.47
2	C.C Drain	M20	06-11-2021	18-11-2021	150x150x150	22500	466	16.5	
3	C.C Drain	M20	06-11-2021	18-11-2021	150x150x150	22500	463	16.7	

Remarks :

AARTN ASSOCIATES BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) | Date: 18-11-2021

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	06-11-2021
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 7 Days Compressive Strength
Date of Test	18-11-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	06-11-2021	18-11-2021	150x150x150	22500	463	16.58	16.71
2	C.C Drain	M20	06-11-2021	18-11-2021	150x150x150	22500	473	16.44	
3	C.C Drain	M20	06-11-2021	18-11-2021	150x150x150	22500	470	17.11	

Remarks :

AARTN ASSOCIATES DATE BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) | Date: 22-11-2021

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	15-11-2021
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 7 Days Compressive Strength
Date of Test	22-11-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	15-11-2021	22-11-2021	150x150x150	22500	470	16.52	16.40
2	C.C Drain	M20	15-11-2021	22-11-2021	150x150x150	22500	480	16.23	
3	C.C Drain	M20	15-11-2021	22-11-2021	150x150x150	22500	473	16.44	

Remarks :

AARTN ASSOCIATES BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 22-11-2021

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	15-11-2021
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 7 Days Compressive Strength
Date of Test	22-11-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	15-11-2021	22-11-2021	150x150x150	22500	460	16.52	16.40
2	C.C Drain	M20	15-11-2021	22-11-2021	150x150x150	22500	471	16.44	
3	C.C Drain	M20	15-11-2021	22-11-2021	150x150x150	22500	457	16.23	

Remarks :

AARTN ASSOCIATES DATE BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) | Date: 23-02-2022

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	16-02-2021
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 7 Days Compressive Strength
Date of Test	23-02-2022
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in K.N	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	16-02-2021	23-02-2022	150x150x150	22500	467	16.67	16.45
2	C.C Drain	M20	16-02-2021	23-02-2022	150x150x150	22500	477	16.25	
3	C.C Drain	M20	16-02-2021	23-02-2022	150x150x150	22500	464	16.44	

Remarks :

AARTN ASSOCIATES DATE BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 23-02-2022

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	16-02-2022
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 7 Days Compressive Strength
Date of Test	23-02-2022
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	16-02-2022	23-02-2022	150x150x150	22500	466	16.89	16.82
2	C.C Drain	M20	16-02-2022	23-02-2022	150x150x150	22500	476	16.25	
3	C.C Drain	M20	16-02-2022	23-02-2022	150x150x150	22500	463	17.33	

Remarks :

AARTN ASSOCIATES DATE BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 17-06-2022

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	10-06-2022
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 7 Days Compressive Strength
Date of Test	17-06-2022
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	10-06-2022	17-06-2022	150x150x150	22500	473	16.25	16.30
2	C.C Drain	M20	10-06-2022	17-06-2022	150x150x150	22500	483	16.44	
3	C.C Drain	M20	10-06-2022	17-06-2022	150x150x150	22500	476	16.22	

Remarks :

AARTN ASSOCIATES BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 17-06-2022

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	10-06-2022
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 7 Days Compressive Strength
Date of Test	17-06-2022
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	10-06-2022	17-06-2022	150x150x150	22500	488	16.25	16.01
2	C.C Drain	M20	10-06-2022	17-06-2022	150x150x150	22500	498	15.25	
3	C.C Drain	M20	10-06-2022	17-06-2022	150x150x150	22500	485	16.52	

Remarks :

AARTN ASSOCIATES BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1659, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) | Date: 06-08-2022

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	30-07-2022
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 7 Days Compressive Strength
Date of Test	06-08-2022
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	10-6-22 30-07-2022	7 days 06-08-2022	150x150x150	22500	466	16.14	16.28
2	C.C Drain	M20	10/6/22 30-07-2022	06-08-2022	150x150x150	22500	476	16.35	
3	C.C Drain	M20	10/6/22 30-07-2022	06-08-2022	150x150x150	22500	469	16.35	

Remarks :

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 06-08-2022

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	30-07-2021
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 7 Days Compressive Strength
Date of Test	06-08-2022
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	10/8/22 30-07-2021	7days 06-08-2022	150x150x150	22500	456	16.35	16.32
2	C.C Drain	M20	10/8/22 30-07-2021	06-08-2022	150x150x150	22500	466	16.25	
3	C.C Drain	M20	10/8/22 30-07-2021	06-08-2022	150x150x150	22500	452	16.35	

Remarks :

AARTN ASSOCIATES BANGALORE

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) | Date: 09-12-2021

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	06-11-2021
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 28 Days Compressive Strength
Date of Test	09-12-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm²	N/mm²
1	C.C Drain	M20	06-11-2021	09-12-2021	150x150x150	22500	695	22.8	22.51
2	C.C Drain	M20	06-11-2021	09-12-2021	150x150x150	22500	705	22.5	
3	C.C Drain	M20	06-11-2021	09-12-2021	150x150x150	22500	698	22.2	

Remarks :

AARTN ASSOCIATES BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) | Date: 09-12-2021

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	06-11-2021
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 28 Days Compressive Strength
Date of Test	09-12-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	06-11-2021	09-12-2021	150x150x150	22500	8.92	692	23.1	22.81
2	C.C Drain	M20	06-11-2021	09-12-2021	150x150x150	22500	9.07	703	22.5	
3	C.C Drain	M20	06-11-2021	09-12-2021	150x150x150	22500	9.13	689	22.9	

Remarks :

AARTN ASSOCIATES BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 13-12-2021

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	15-11-2021
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 28 Days Compressive Strength
Date of Test	13-12-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Weight of the sample	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	kg	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	15-11-2021	13-12-2021	150x150x150	22500	8.72	682	20.15	21.47
2	C.C Drain	M20	15-11-2021	13-12-2021	150x150x150	22500	8.87	695	22.13	
3	C.C Drain	M20	15-11-2021	13-12-2021	150x150x150	22500	8.62	686	22.14	

Remarks :

AARTN A.A. DATE BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 13-12-2021

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	15-11-2021
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 28 Days Compressive Strength
Date of Test	13-12-2021
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in K.N	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	15-11-2021	13-12-2021	150x150x150	22500	699	30.3	30.02
2	C.C Drain	M20	15-11-2021	13-12-2021	150x150x150	22500	689	29.6	
3	C.C Drain	M20	15-11-2021	13-12-2021	150x150x150	22500	708	30.3	

Remarks :

AARTN ASSOCIATES BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 16-03-2022

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	16-02-2022
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 28 Days Compressive Strength
Date of Test	16-03-2022
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	16-02-2022	16-03-2022	150x150x150	22500	690	30.7	30.71
2	C.C Drain	M20	16-02-2022	16-03-2022	150x150x150	22500	700	30.3	
3	C.C Drain	M20	16-02-2022	16-03-2022	150x150x150	22500	687	31.2	

Remarks :

AARTN ASSOCIATES BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 16-03-2022

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	16-02-2022
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 28 Days Compressive Strength
Date of Test	16-03-2022
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	16-02-2022	16-03-2022	150x150x150	22500	695	31.3	31.64
2	C.C Drain	M20	16-02-2022	16-03-2022	150x150x150	22500	705	31.3	
3	C.C Drain	M20	16-02-2022	16-03-2022	150x150x150	22500	692	32.3	

Remarks :

AARTN ASSOCIATES BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) | Date: 08-07-2022

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	10-06-2022
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 28 Days Compressive Strength
Date of Test	08-07-2022
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	10-06-2022	08-07-2022	150x150x150	22500	696	30.3	30.84
2	C.C Drain	M20	10-06-2022	08-07-2022	150x150x150	22500	707	31.5	
3	C.C Drain	M20	10-06-2022	08-07-2022	150x150x150	22500	693	30.8	

Remarks :

AARTN ASSOCIATES BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) | Date: 08-07-2022

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	10-06-2022
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 28 Days Compressive Strength
Date of Test	08-07-2022
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm^2	N/mm^2
1	C.C Drain	M20	10-06-2022	08-07-2022	150x150x150	22500	699	31.3	30.92
2	C.C Drain	M20	10-06-2022	08-07-2022	150x150x150	22500	689	30.7	
3	C.C Drain	M20	10-06-2022	08-07-2022	150x150x150	22500	705	30.9	

Remarks :

AARTN ASSOCIATES BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) | Date: 27-07-2022

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	30-07-2022 ~~30/6/22~~ 10/6/22
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 28 Days Compressive Strength
Date of Test	27-07-2022
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm²	N/mm²
1	C.C Drain	M20	10/06/22 ~~30-07-2022~~	07/7/22 27-07-2022	150x150x150	22500	698	32.3	31.69
2	C.C Drain	M20	10/06/22 ~~30-07-2022~~	07/7/22 27-07-2022	150x150x150	22500	706	31.3	
3	C.C Drain	M20	10/06/22 ~~30-07-2022~~	07/7/22 27-07-2022	150x150x150	22500	703	31.6	

Remarks :

AARTN ASSOCIATES DATE BANGALORE

AARTN ASSOCIATES

The Modern Construction Solutions

#1059, MIG-A Sector, Opp. Railwheel Factory,
Yelahanka New Town, Bangalore - 64
Ph : 8048505503 | Email : aartnassociates@gmail.com

Test Report of Cement Concrete Cubes

IS: 516-1959 (Method of tests for strength of Concrete C1.5) — Date: 27-07-2022

Name of Work : Comprehensive Development of Hegdenagar East Side cross roads and Shabarinagar Cross road in Ward No.06

Client	Bruhat Bengalore Mahanagara Palike (BBMP) , Yelahanka Zone, Bengaluru.
Contractor	Sri. V Chandrappa
Customer Reference	EE(Project)YNK Zone/WO/163/2019-20
Source of Sample	Sample supplied by Agency
Sample Condition	Satisfactory
Date of Reciept	30-07-2022 ~~(30-6-22)~~ 10/6/22
Sample Type	C.C Drain
Sample Type/Size	150x150x150 mm
Sample Grade/ Age	M20/ 28 Days Compressive Strength
Date of Test	27-07-2022
Location	

Sl No.	Identification Mark	Grade of Concrete	Date of Casting	Date of Trsting	Dimension of Specification	Cross sectional area	Maximum Load in	Compressive Strength	Average Compressive Strength
					mm	Sq.mm	KN	N/mm²	N/mm²
1	C.C Drain	M20	~~30-6-22~~ 30-07-2022	07/7/22 27-07-2022	150x150x150	22500	700	31.7	31.25
2	C.C Drain	M20	~~30-6-22~~ 30-07-2022	07/7/22 27-07-2022	150x150x150	22500	694	30.3	
3	C.C Drain	M20	~~30-6-22~~ 30-07-2022	07/7/22 27-07-2022	150x150x150	22500	697	31.9	

Remarks :

AARTN ASSOCIATES DATE BANGALORE